



**Test Report**

**No: GZFD0100702856FD-1**

**Date: Aug. 03, 2010**

Client name : BestSub Technologies Co., Ltd.

Client address: Rm 8A01, Jinzhou International Business Center, NO. 899 Jiefangbei Rd, Guangzhou, 510015, China

**The following sample(s) was/were submitted by/ on behalf of the client as:**

Sample Name: 14OZ Stainless Steel Mug

Batch/Date: /

Manufacturer: /

SGS reference no.: GZ1007084135/CHEM

SGS job no.: GZFD0100702856FD-1

Date of receipt: Jul. 21, 2010

Testing period: Jul. 21, 2010 ~ Jul. 29, 2010

**TEST(S) REQUESTED:**

Selected test(s) as requested by applicant:

As specified by client, selected parts of the submitted sample(s) for compliance with Public Law 110-314 (Consumer Product Safety Improvement Act of 2008, CPSIA):-

- 1) Lead in paint / similar surface coating material
- 2) Lead in accessible substrate materials
- 3) Phthalates

**TEST METHOD(S):**

- 1) CPSC Test Method: CPSC-CH-E1003-09 'Standard Operation Procedure for Determining Total Lead (Pb) in paint and other similar surface coating'.
- 2) Method (metal materials): CPSC Test Method: CPSC-CH-E1001-08 'Standard Operating Procedure for Determining Total Lead (Pb) in Children's Metal Products (Including Children's Metal Jewelry)'.
- 3) With reference to ASTM D3421-75. Analysis was performed by Gas Chromatography / Mass Spectrometry.

**TEST RESULT(S):**

Please refer to next page(s).

**SUMMARY:**

Item	Test Parameter	Conclusion
1	CPSIA section 101(f) - Lead in paint/similar surface coating material	PASS
2	CPSIA section 101(a)(2) - Lead in accessible substrate materials	PASS
3	CPSIA section 108 - Phthalates	PASS

Signed for and on behalf of SGS

Authorized Signature

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To ensure the authenticity of testing/inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

**GZFD**

**TEST RESULT(S):**

1) Lead in paint/similar surface coating material

Test Item	Test Result	Method Detection Limit	Permissible Limit	Comment
	#1			
Lead (Pb)	Not detected	0.002 %	0.009 %	PASS

Note: 1. % = percentage by weight  
 2. 1% = 10000ppm (mg/kg)  
 3. The result(s) of #1 shown is/are of the total weight of wet sample.

2) Lead in accessible substrate materials

Test Item	Test Result	Method Detection Limit	Permissible Limit**	Comment
	#2			
Lead (Pb)	Not detected	0.002 %	0.03 %	PASS

\*\*The requirements for lead in substrate in children's products is summarized below

Scope	Requirement	Effective date
Lead in accessible substrate	≤ 0.03 %	14 August 2009
	≤ 0.01%	14 August 2011

Note: 1. % = percentage by weight  
 2. 1% = 10000ppm (mg/kg)

3) Phthalates

Concentration of phthalates in components of toy that can be placed in the mouth or childcare article

Test item	Test Result	Permissible Limit per component	Method Detection Limit	Comment
	#1			
Dibutyl Phthalate (DBP)	Not detected	0.1%	0.003 %	PASS
Benzylbutyl Phthalate (BBP)	Not detected	0.1%	0.003 %	PASS
Bis-(2-ethylhexyl) Phthalate (DEHP)	0.047%	0.1%	0.003 %	PASS
Diisononyl Phthalate (DINP)	Not detected	0.1%	0.01 %	PASS
Di-n-octyl Phthalate (DNOP)	Not detected	0.1%	0.003 %	PASS
Diisodecyl Phthalate (DIDP)	Not detected	0.1%	0.01 %	PASS

Note: 1. % = percentage by weight  
 2. 1% = 10000ppm (mg/kg)  
 3. The result(s) of #1 shown is/are of the total weight of wet sample.

Remark: Test results in this report are applicable for the item tested and reflects the tested sample as received.

Test Report

No: GZFDO100702856FD-1

Date: Aug. 03, 2010

**SAMPLE DESCRIPTION:** #1: Transparent paste in bottle (used for steel mug, raw material), #2: Silver-grey metal (base of transparent coated metal) (steel mug, finished product)

### Photo Appendix



#1



#2

SGS authenticate the photo on original report only

\*\*\* End of Report\*\*\*